



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-25-11-26-03843-001-01

Date: 2025-11-26

Client : Chandpur Road Division Lab Register No. : 19 (B) 2025-2026.
Tender No. : 1005143 Contract No. : e-GP/PMPRoad/Chandpur/CZ-01/2024-2025
Tracking Number : LAB-25-11-26-03843 Sample Sent By : Client
Project/Work Name : Periodic Maintenance Programme (PMP) by Strengthening Work, DBS Wearing Course, Protective Work and Earth Work From Ch.54+000 (Bakila Bazar) to Ch. 70+178m (Bagadi Chowrasta) of Cumilla-Lalmal-Chandpur-Laxmipur-Begumgonj) (R-140) Road under Road Division,
Sample Collection From : From Stackyard Sample Source : Nill
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)
Name of Test : BITUMEN ROUTINE TEST Test Code : BRRL
Item Name : Others
Test Method : ASTM
Associated Agency : M/S. Shahid Brothers-M/S OK Enterprise JV, Address: Toragar, Haziganj, Chandpur.
Date of sample receive : 19/11/2025 Date of Test : 20/11/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division Chandpur.
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafiur Nur Mousum
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	85		ASTM D-5	60 - 70	80/100
Softening Point	°C	46		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.09		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	80.59		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	320		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.389				
Weight of Pycnometer +Water, B	gm	56.131				
Weight Pycnometer partially filled with Bitumen, C	gm	44.842				
Pycnometer+Bitmen+Water, D	gm	56.285				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0108				
Specific Gravity		1.0108				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

26-Nov-2025

Akram Hossen
Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

26-Nov-2025

Sheikh Nafiur Nur Mousum
Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

26-Nov-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

26-Nov-2025

Shamima Yasmin
Executive Engineer
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.