



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-25-12-08-03844-001-01

Date: 2025-12-08

Client : Feni Road Division Lab Register No. : 20 (B) 2025-2026.
Tender No. : 1151427 Contract No. : GP/Rev/OTM/Work/FRD-05/2025-2026
Tracking Number : LAB-25-12-08-03844 Sample Sent By : Client
Project/Work Name : Restoration of Damaged Pavement by Carpeting & Seal Coat repair work at Chainage 0+000 to 0+150 km of Shuvapur Old Feryghat Link Road (Z-1020) Under Feni Road Division, during the year 2025-2026.
Sample Collection From : From Stackyard Sample Source : Null
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others Test Code : BRRL
Test Method : ASTM
Associated Agency : Md. MOYENUDDIN (BASHI) LIMITED.
Date of sample receive : 03/12/2025 Date of Test : 07/12/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Feni Road Division.
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafur Nur Mousum
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	67		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.08		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	82.09		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	300		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.370				
Weight of Pycnometer +Water, B	gm	56.136				
Weight Pycnometer partially filled with Bitumen, C	gm	44.832				
Pycnometer+Bitmen+Water, D	gm	56.421				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity= $((C-A)/((B-A)-(D-C)))*(GT/G25)$		1.0201				
Specific Gravity		1.0201				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

09-Dec-2025

Akram Hossen
Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

09-Dec-2025

Sheikh Nafur Nur Mousum
Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

09-Dec-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

09-Dec-2025

Shamima Yasmin
Executive Engineer
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.