



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-25-03-02-03744-001-01

Date: 2025-03-02

Client : Munshiganj Road Division Lab Register No. : 74 (B) 2024-2025.
Tender No. : 1058106 Contract No. : 18/e-GP/EE/MRD/2024-2025
Tracking Number : LAB-25-03-02-03744 Sample Sent By : Client
Project/Work Name : Renovation of Roundabout at Ch. 0+029m (Zero Point) of 'Dhaka-Mawa-Bhanga Expressway (N-8)' under
Munshiganj Road Division, Munshiganj during the year 2024-2025.
Sample Collection From : From Stackyard Sample Source : Nill
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others Test Code : BRRL
Test Method : ASTM
Associated Agency : M/S R.P. Construction Co.32/A, Navana Garden, Kallanpur, Dhaka.
Date of sample receive : 26/02/2025 Date of Test : 27/02/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount
of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Munshiganj
Road Division, Munshiganj .
Test Performed By : Akram Hossen Test Supervised By : Mst. Rupali Khatun
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	68		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.07		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	86.76		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	312		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.382				
Weight of Pycnometer +Water, B	gm	55.187				
Weight Pycnometer partially filled with Bitumen, C	gm	45.896				
Pycnometer+Bitmen+Water, D	gm	55.518				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0218				
Specific Gravity		1.0218				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

02-Mar-2025

Akram Hossen
Assistant Research Officer
(Additional Charge)
Quality Control & Training
Division, BRRL

Test Approved By

02-Mar-2025

Mst. Rupali Khatun
Assistant Engineer
(Additional Charge)
Quality Control & Training
Division, BRRL

Counter Signed By

02-Mar-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

02-Mar-2025

Shamima Yasmin
Executive Engineer
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.