

Government of the Peoples Republic of Bangladesh Quality Control & Training Division, BRRL

DATA & REPORT SHEET

Memo No: LAB-25-03-10-03751-001-01 Date: 2025-03-10

Client : Madaripur Road Dvision Lab Register No. : 81 (B) 2024-2025.

Tender No. : 1031644 Contract No. : e-GP/08/EE/MRD/PMP-

Minor/2024-2025

Tracking Number : LAB-25-03-10-03751 Sample Sent By : Client

Project/Work Name : Seal Coat & Undulation, Depression Repair work at Ch.11+250 to 11+280, Ch.11+380 to 11+420,

Ch.11+490 to 11+500, Ch.11+600 to 11+650, Ch.11+720 to 11+740, Ch.12+500 to 12+600, Ch.12+650 to

12+780, Ch.12+800 to 13+000, Ch.13+300 to 13+550, Ch.13+700 to 13

Sample Collection From : From Stackyard Sample Source : Nill

Sample Sealing Status : Sealed Sample Collected By : EE (RHD)

Name of Test : BITUMEN ROUTINE TEST

Item Name : Others Test Code : BRRL

Test Method : ASTM

Associated Agency : Md Zinnat Hoassain Biswas, Kamlapur Faridpur.

Date of sample receive : 06/03/2025 Date of Test : 09/03/2025

at Lab

Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount

of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division,

Madaripur.

Test Performed By : Akram Hossen Test Supervised By : Mst. Rupali Khatun

Assistant Research Officer

BITUMEN ROUTINE TEST

| Name of the test | Unit | Result | Comments | Test Code | Spec 60/70 | Spec 80/100 |
|--|-------------------|-------------|-------------|------------|------------|-------------|
| Penetration @25°C (100g, 5s) | 0.1mm | 83 | | ASTM D-5 | 60 - 70 | 80/100 |
| Softening Point | °C | 45 | | ASTM D-36 | 48 - 56 | 45 - 52 |
| Ductility (@25°C) | CM | 100 | | ASTM D-113 | ≥ 100cm | ≥ 100cm |
| Loss on heating | %(of wt) | 0.06 | | ASTM D-6 | ≤ 0.2 | ≤ 0.5 |
| Penetrating drop after heating | % | 86.75 | | ASTM D-5&6 | ≥ 80 | ≥ 80 |
| Flash point | °C | 320 | | ASTM D-92 | ≥ 250 | ≥ 250 |
| Specific Gravity @25/25°C | | | | | | |
| Descriptions | Unit | Specimen #1 | Specimen #2 | | | |
| Weight of Pycnometer (+Stopper), A | gm | 30.389 | | | | |
| Weight of Pycnometer +Water, B | gm | 55.187 | | | | |
| Weight Pycnometer partially filled with Bitumen, C | gm | 45.897 | | | | |
| Pycnometer+Bitmen+Water, D | gm | 55.508 | | | | |
| Density of Water at 25 °C, G25 | Kg/m ³ | 1000 | | | | |
| Temperature of Water (T); °C, | °C | 25 | | | | |
| Density of Water at Temperature T °C(GT) | Kg/m ³ | 1000 | | | | |
| SP. Gravity=((C-A)/{(B-A)-(D-C)})*(GT/G25) | | 1.0211 | | | | |
| Specific Gravity | | 1.0211 | | | | |

Comment: Test was performed on the basis of supplied sample.

HORAN

Test Performed By

Akram Hossen Assistant Research Officer (AC) Quality Control & Training Division, BRRL

10-Mar-2025

Test Approved By

10-Mar-2025 Mst. Rupali Khatun Assistant Engineer (AC) Quality Control & Training Division, BRRL Counter Signed By

10-Mar-2025 Jahangir Alam Sub Divisional Engineer Quality Control & Training Division, BRRL Counter Signed By

10-Mar-2025
Shamima Yasmin
Executive Engineer
Quality Control & Training

Division, BRRL