



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-25-03-18-03757-001-01

Date: 2025-03-18

Client : Gazipur Road Division
Tender No. : 1049308
Tracking Number : LAB-25-03-18-03757
Project/Work Name : Repair, Carpeting & SBST work at 1st km, 2nd km, 3rd km, 4th km, 5th km (p) km of Kaliganj (Tumulia Mission Mor)-Bortul-Khaisair (Danga) Road under Gazipur Road Division during the year 2024-2025.
Sample Collection From : From Stackyard
Sample Sealing Status : Sealed
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others
Test Method : ASTM
Associated Agency : M/S. DELUXE ENTERPRISE, A-58, Mohakhali Bazar, Gulshan, Dhaka.
Date of sample receive : 06/03/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division, Gazipur .
Test Performed By : Akram Hossen
Assistant Research Officer
Lab Register No. : 88 (B) 2024-2025.
Contract No. : e-GP/19/GRD/2024-2025
Sample Sent By : Client
Sample Source : Nill
Sample Collected By : EE (RHD)
Test Code : BRRL
Date of Test : 17/03/2025
Test Supervised By : Mst. Rupali Khatun

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	67		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.08		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	86.57		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	318		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.390				
Weight of Pycnometer +Water, B	gm	55.179				
Weight Pycnometer partially filled with Bitumen, C	gm	45.828				
Pycnometer+Bitmen+Water, D	gm	55.517				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0224				
Specific Gravity		1.0224				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

18-Mar-2025

Akram Hossen
Assistant Research Officer (AC)
Quality Control & Training
Division, BRRL

Test Approved By

18-Mar-2025

Mst. Rupali Khatun
Assistant Engineer (AC)
Quality Control & Training
Division, BRRL

Counter Signed By

18-Mar-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

18-Mar-2025

Shamima Yasmin
Executive Engineer
Quality Control & Training
Division, BRRL