



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-25-05-29-03797-001-01

Date: 2025-05-29

Client : Comilla Road Division
Tender No. : 1098114
Tracking Number : LAB-25-05-29-03797
Project/Work Name : Repair of Broken edge & Damaged Road Surface Providing Carpeting, Photoles Repair, SBST work at 1st (P) Km to 7th (P) Km Laksham (Binoighar)-Baiaarabazar-Omaranj-Nangalkot Road (Z-1415) under Road Division Cumilla, during the year 2024-2025.
Sample Collection From : From Stackyard
Sample Sealing Status : Sealed
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others
Test Method : ASTM
Associated Agency : M/s. TAJ Enterprise, South Chartha, Adarsha Sadar, Cumilla.
Date of sample receive : 27/05/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division, Cumilla.
Test Performed By : Akram Hossen
Assistant Research Officer
Lab Register No. : 121 (B) 2024-2025.
Contract No. : GP-78/CRD/LTM/2024-2025
Sample Sent By : Client
Test Code : BRRL
Sample Collected By : EE (RHD)
Date of Test : 28/05/2025
Test Supervised By : Sheikh Nafiur Nur Mousum

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	68		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.08		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	85.29		ASTM D-586	≥ 80	≥ 80
Flash point	°C	310		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.375				
Weight of Pycnometer +Water, B	gm	56.140				
Weight Pycnometer partially filled with Bitumen, C	gm	44.831				
Pycnometer+Bitmen+Water, D	gm	56.439				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C.	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0211				
Specific Gravity		1.0211				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

29-May-2025

Akram Hossen
Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

29-May-2025

Sheikh Nafiur Nur Mousum
Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

29-May-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

29-May-2025

Dewan Md. Abdul Kader
Executive Engineer(AC)
Quality Control & Training
Division, BRRL