



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL

DATA & REPORT SHEET



Memo No: LAB-25-06-03-03809-001-01

Date: 2025-06-03

Client : Comilla Road Division
Tender No. : 1098110
Tracking Number : LAB-25-06-03-03809
Project/Work Name : Repair of Damaged Road Surface Providing Carpeting, Photoles Repair, SBST work at 6th (P), 7th (P), 8th (P), 9th (P), 11th (P), 12th (P) & 13th (P) Km Harishchar-Kashinagar-Miabazar Road (Z-1046) under Road Division Cumilla, during the year 2024-2025.
Sample Collection From : From Stackyard
Sample Sealing Status : Sealed
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others
Test Method : ASTM
Associated Agency : M/s. Munshi Enterprise, New Bagisagaon, Station Road, Adarsha Sadar, Cumilla.
Date of sample receive : 29/05/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 7 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division, Cumilla.
Test Performed By : Akram Hossen
Assistant Research Officer
Lab Register No. : 135 (B) 2024-2025.
Contract No. : GP-74/CRD/LTM/2024-2025
Sample Sent By : Client
Test Code : BRRL
Sample Source : Nill
Sample Collected By : EE (RHD)
Date of Test : 01/06/2025
Test Supervised By : Sheikh Nafiur Nur Mousum

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	62		ASTM D-5	60 - 70	80/100
Softening Point	°C	50		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.05		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	83.55		ASTM D-586	≥ 80	≥ 80
Flash point	°C	322		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.384				
Weight of Pycnometer +Water, B	gm	56.137				
Weight Pycnometer partially filled with Bitumen, C	gm	44.828				
Pycnometer+Bitmen+Water, D	gm	56.432				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C.	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0208				
Specific Gravity		1.0208				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

03-Jun-2025

Akram Hossen
Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

03-Jun-2025

Sheikh Nafiur Nur Mousum
Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

03-Jun-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

03-Jun-2025

Dewan Md. Abdul Kader
Executive Engineer(AC)
Quality Control & Training
Division, BRRL