



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL

DATA & REPORT SHEET



Memo No: LAB-25-06-22-03818-001-01

Date: 2025-06-22

Client : Gazipur Road Division
Tender No. : 1050365
Tracking Number : LAB-25-06-22-03818
Project/Work Name : Periodic Maintenance Programe for DBS Wearing Course work from Ch. 12+550m to Ch. 16+053m. Ch. 16+286m to Ch. 18+000m and Ch. 21+140m to Ch. 25+450m of Kapasia-Pabur-Fuldi-Kaliganj Road under Gazipur Road Division, during the year 2023-2024.
Sample Collection From : From Stackyard
Sample Sealing Status : Sealed
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others
Test Method : ASTM
Associated Agency : HREDI Construction Ltd.- MS Moni Enterprise- (JV), 827/1, 2nd Floor, Begum Rokeya Sarani Shewrapara, Mirpur, Dhaka.
Date of sample receive : 16/06/2025
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 5 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division, Gazipur.
Test Performed By : Akram Hossen
Assistant Research Officer
Lab Register No. : 144 (B) 2024-2025.
Contract No. : PMP/e-Gp/23/GRD/2024-2025
Sample Sent By : Client
Sample Source : Nill
Sample Collected By : EE (RHD)
Test Code : BRRL
Date of Test : 19/06/2025
Test Supervised By : Sheikh Nafiur Nur Mousum

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	70		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.06		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	82.86		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	300		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.380				
Weight of Pycnometer +Water, B	gm	56.135				
Weight Pycnometer partially filled with Bitumen, C	gm	44.827				
Pycnometer+Bitmen+Water, D	gm	56.307				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T): °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0120				
Specific Gravity		1.0120				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

22-Jun-2025

Akram Hossen
Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

22-Jun-2025

Sheikh Nafiur Nur Mousum
Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

22-Jun-2025

Jahangir Alam
Sub Divisional Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

22-Jun-2025

Dewan Md. Abdul Kader
Executive Engineer(AC)
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.