



Government of the Peoples Republic of Bangladesh  
Quality Control & Training Division, BRRL

DATA & REPORT SHEET

Memo No: LAB-26-04-16-03887-001-01

Date: 2026-04-16

Client : Munshiganj Road Division Lab Register No. : 68 (B) 2025-2026.  
Tender No. : 1231124 Contract No. : 47/e-GP/EE/MRD/2025-2026  
Tracking Number : LAB-26-04-16-03887 Sample Sent By : Client  
Project/Work Name : Repair of Existing Pavement by Aggregate base type-1, carpeting and seal coat work at Ch. 7+935 to Ch. 8+685 of Rikabibazar-Rampal-Dighirpar-Banglabazar- Munshigonj-Mukterpur Road (Z-8121) under Munshigonj Road Division during the year 2025-2026.  
Sample Collection From : From Stackyard Sample Source : Nill  
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)  
Name of Test : BITUMEN ROUTINE TEST Test Code : BRRL  
Item Name : Others  
Test Method : ASTM  
Associated Agency : M/S.M.H Mainuddin Construction, Address BIWTB Staff Quarter Road, Kotwali, Chattogram.  
Date of sample receive : 12/04/2026 Date of Test : 19/04/2026  
at Lab  
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 5 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division Munshigonj.  
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafur Nur Mousum  
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	67		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.09		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	81.18		ASTM D-586	≥ 80	≥ 80
Flash point	°C	295		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.364				
Weight of Pycnometer +Water, B	gm	56.138				
Weight Pycnometer partially filled with Bitumen, C	gm	44.821				
Pycnometer+Bitmen+Water, D	gm	56.429				
Density of Water at 25 °C, G25	Kg/m <sup>3</sup>	1000				
Temperature of Water (T); °C.	°C	25				
Density of Water at Temperature T °C( GT )	Kg/m <sup>3</sup>	1000				
SP. Gravity=((C-A)/((B-A)-(D-C)))*(GT/G25)		1.0205				
Specific Gravity		1.0205				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

20-Apr-2026

Akram Hossen

Assistant Research Officer(AC)  
Quality Control & Training  
Division, BRRL

Test Approved By

20-Apr-2026

Sheikh Nafur Nur Mousum

Assistant Engineer  
Quality Control & Training  
Division, BRRL

Counter Signed By

20-Apr-2026

Sheikh Nafur Nur Mousum

Sub Divisional Engineer(AC)  
Quality Control & Training  
Division, BRRL

Counter Signed By

20-Apr-2026

Dewan Abul Kashem  
Mohammad Nahin Reza  
Executive Engineer  
Quality Control & Training  
Division, BRRL

This is a auto generated report by OLTMS system.