



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-26-04-16-03889-001-01

Date: 2026-04-16

Client : Munshiganj Road Division Lab Register No. : 70 (B) 2025-2026.
Tender No. : 1157673 Contract No. : 43/e-GP/EE/MRD/2025-2026
Tracking Number : LAB-26-04-16-03889 Sample Sent By : Client
Project/Work Name : Periodic Maintenance Programme for Construction of Rigid Pavement, HBB work & DBS-Wearing Course from Ch. 0+895m to Ch.5+000m of Hasnabad Intersection to Pangaon Container Terminal Road (N-810) under Munshigonj Road Division during the year 2025-2026.
Sample Collection From : From Stackyard Sample Source : Nill
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)
Name of Test : BITUMEN ROUTINE TEST Test Code : BRRL
Item Name : Others
Test Method : ASTM
Associated Agency : Tanvir Construction Ltd, Address: Rahman's Regnum Centre (10th Floor), 19*1/1 Tejgaon Gulshan Link Road, Tejgaon C/A, Dhaka-1208.
Date of sample receive : 12/04/2026 Date of Test : 13/04/2026
at Lab
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 5 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division Munshigonj.
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafiur Nur Mousum
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	65		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.06		ASTM D-6	≤ 0.2	≤ 0.5
Penetrating drop after heating	%	89.23		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	315		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.376				
Weight of Pycnometer +Water, B	gm	56.137				
Weight Pycnometer partially filled with Bitumen, C	gm	44.831				
Pycnometer+Bitmen+Water, D	gm	56.422				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity= $\frac{(C-A)}{(B-A)-(D-C)} \times (GT/G25)$		1.0201				
Specific Gravity		1.0201				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

20-Apr-2026

Akram Hossen

Test Approved By

20-Apr-2026

Sheikh Nafiur Nur Mousum

Counter Signed By

20-Apr-2026

Sheikh Nafiur Nur Mousum

Counter Signed By

20-Apr-2026

Dewan Abul Kashem
Mohammad Nahin Reza
Executive Engineer
Quality Control & Training
Division, BRRL

Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Assistant Engineer
Quality Control & Training
Division, BRRL

Sub Divisional Engineer(AC)
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.