



Government of the Peoples Republic of Bangladesh
Quality Control & Training Division, BRRL



DATA & REPORT SHEET

Memo No: LAB-26-05-04-03899-001-01

Date: 2026-05-04

Client : Gazipur Road Division Lab Register No. : 82 (B) 2025-2026.
Tender No. : 1220328 Contract No. : GP 33/GRD/Minor/2025-2026
Tracking Number : LAB-26-05-04-03899 Sample Sent By : Client
Project/Work Name : Repair with Carpeting Seal coat work and Uni-Blok work for Rail gate at Ch. 0+000m to 01+600m of Kaliakoir Town old Section Road (N-406) under Gazipur Road Division during the year 2025-2026.
Sample Collection From : From Stackyard Sample Source : Nill
Sample Sealing Status : Sealed Sample Collected By : EE (RHD)
Name of Test : BITUMEN ROUTINE TEST
Item Name : Others Test Code : BRRL
Test Method : ASTM
Associated Agency : PEU ENTERPRISE, Tarashi, Kotalipara, Gopalganj.
Date of sample receive at Lab : 26/04/2026 Date of Test : 03/05/2026
Sample Description : Sample was supplied to the laboratory by Contractor's representative. Sample was carried in a pot. Amount of sample received is 5 kg approximately. Sample was sealed by Executive Engineer, RHD, Road Division Gazipur.
Test Performed By : Akram Hossen Test Supervised By : Sheikh Nafiur Nur Mousum
Assistant Research Officer

BITUMEN ROUTINE TEST

Name of the test	Unit	Result	Comments	Test Code	Spec 60/70	Spec 80/100
Penetration @25°C (100g, 5s)	0.1mm	67		ASTM D-5	60 - 70	80/100
Softening Point	°C	48		ASTM D-36	48 - 56	45 - 52
Ductility (@25°C)	CM	100		ASTM D-113	≥ 100cm	≥ 100cm
Loss on heating	%(of wt)	0.08		ASTM D-6	≤ 0.2	≤ 0.5
Penetration of residue from loss on heating test at 25°C, 100g, 5 Sec, as compared to penetration before heating	%	84.35		ASTM D-5&6	≥ 80	≥ 80
Flash point	°C	305		ASTM D-92	≥ 250	≥ 250
Specific Gravity @25/25°C						
Descriptions	Unit	Specimen #1	Specimen #2			
Weight of Pycnometer (+Stopper), A	gm	30.368				
Weight of Pycnometer +Water, B	gm	56.133				
Weight Pycnometer partially filled with Bitumen, C	gm	44.834				
Pycnometer+Bitmen+Water, D	gm	56.427				
Density of Water at 25 °C, G25	Kg/m ³	1000				
Temperature of Water (T); °C,	°C	25				
Density of Water at Temperature T °C(GT)	Kg/m ³	1000				
SP. Gravity= $\frac{(C-A)}{(B-A)-(D-C)} \times (GT/G25)$		1.0207				
Specific Gravity		1.0207				

Comment : Test was performed on the basis of supplied sample.

Test Performed By

04-May-2026

Akram Hossen

Assistant Research Officer(AC)
Quality Control & Training
Division, BRRL

Test Approved By

04-May-2026

Sheikh Nafiur Nur Mousum

Assistant Engineer
Quality Control & Training
Division, BRRL

Counter Signed By

04-May-2026

Mahbuba Akter

Sub Divisional Engineer(AC)
Quality Control & Training
Division, BRRL

Counter Signed By

04-May-2026

Dewan Abul Kashem
Mohammad Nahin Reza
Executive Engineer
Quality Control & Training
Division, BRRL

This is a auto generated report by OLTMS system.